



PRODUCT PROFILE
2100 INTERIOR/EXTERIOR
ROCKPOXY GLOSS ENAMEL
100% ACRYLIC

1950 Dr. Martin Luther King Jr. Pkwy. - Chico, Ca 95928 - (530) 345-9595 - Fax (530) 345-3589

DESCRIPTION:

2100 Rockpoxy gloss latex is a fast drying 100% acrylic finish for all kinds of primed or pre-painted interior and exterior surfaces. 2100 is very resistant to soiling, fading and chalking under extreme weather conditions.

PHYSICAL PROPERTIES	
COLOR	WHITE AND BASES
FINISH	GLOSS
SOLVENT	WATER
DRY TO TOUCH	1-2 HOURS
% SOLIDS BY VOLUME	33%
% SOLIDS BY WEIGHT	47%
COVERAGE	300-400 SQUARE FEET
VISCOSITY	90-95 KREB UNITS
RECOAT TIME	6-12 HOURS

V.O.C.: LESS THAN 250 GRAMS PER LITER

ADVANTAGES:

- * Fast drying
- * Superior color retention
- * Meets clean air standards
- * Flexible strength
- * Water thinned
- * Extremely durable
- * Easy application
- * Outstanding adhesion

**Refer to label for cautions and warnings



PRODUCT PROFILE

2100 INTERIOR/EXTERIOR ROCKPOXY GLOSS ENAMEL 100% ACRYLIC

1950 Dr. Martin Luther King Jr. Pkwy. - Chico, Ca 95928 - (530) 345-9595 - Fax (530) 345-3589

TYPE OF PRODUCT:

A premium quality acrylic GLOSS enamel for general use on INTERIOR and EXTERIOR primed surfaces. Very resistant to soiling, fading and chalking under extreme weather conditions.

TYPICAL USES:

All interior and exterior surfaces where durability and washability are desired. Excellent for cabinets, walls, doors and window trim.

SURFACE PREPARATION:

Be sure all surfaces are dry, free from dirt, grease, wax, chalky paint, rust, efflorescence and stains. Dull or etch glossy, glazed or dense surfaces. Neutralize alkali conditions, remove and kill all mildew or any other contamination that would adversely affect the performance of this coating.

APPLICATION:

May be applied by brush, roller or airless spray equipment. Avoid applying in direct hot sunlight, paint in the shade if possible. Do not apply in temperature below 50°F.

DRYING TIME:

2-4 hours under normal conditions. Recoat 6-12 hours.

PREVIOUSLY PAINTED SURFACES:

Previously painted surfaces in good sound condition do not require priming. Spot prime bare or patched areas or prime entire surface with a suitable Corlin primer. Glossy surfaces should be dulled by sanding or other suitable methods.

NEW SURFACES:

Prime with suitable product for the substrate being painted either alkyd or latex type. Etch new concrete before painting.

COVERAGE:

Approx. 300-400 square feet per gallon, depending on texture porosity of the surface to be painted.

THINNING AND CLEAN-UP:

Formulated ready for use. If thinning is necessary use small amount of water. Do not over thin. Clean brushes and equipment with water immediately after use.

COLORS:

White and Tint Bases

PACKAGE SIZES: 5 gallon, 1 gallon, quarts
APPROX. WEIGHT PER GAL: 10.2 LB.